## EverGuard® TPO 60 mil Membrane Data Sheet

Updated: 6/18



Quality You Can Trust...From North America's Largest Roofing Manufacturer!™

## EverGuard<sup>®</sup> TPO 60 mil Membrane

## **Applicable Standards**

UL Listed, FM Approved, Miami-Dade County Product Control Approved, State of Florida Approved, CRRC Rated, Title 24 Compliant<sup>\*</sup>, ENERGY STAR<sup>®</sup> Certified<sup>\*\*</sup>, ASTM D6878.

Physical Properties	ASTM Test Method	ASTM D6878 Minimum	EverGuard® Typical Test Data				
<ol> <li>Certain data is provided in MD (machine direction) x CMD (cross machine direction) format.</li> <li>Data is based upon typical product performance, and is subject to normal manufacturing tolerance and variance.</li> </ol>							
Nominal Thickness	ASTM D751	0.039" (min.) (0.99 mm)	0.060" (1.52 mm)				
Breaking Strength	ASTM D751 Grab Method	220 lbf/in. (38.5 kn/m)	305 lbf x 290 lbf (454 x 432 kg/m)				
Factory Seam Strength	ASTM D751	66 lbf (98.34 kg/m)	135 lbf (membrane failure) (201.1 kg/m)				
Elongation at Break	ASTM D751	15%	30%				
Heat Aging	ASTM D573	90% Retention of Breaking Strength and Elongation at Break	100%				
Tear Strength	ASTM D751 8" x 8" (203 x 203 mm) Sample	55 lbf (81.95 kg/m)	75 lbf x 130 lbf (111.8 x 193.7 kg/m)				
Puncture Resistance	FTM 101C Method 2031	Not Established	380 lb. (172 kg)				
Cold Brittleness	ASTM D2137	-40°C	-40°C				
Permeance	ASTM E96	Not Established	0.08 Perms				
Dimensional Change	ASTM D1204 @158°F (70°C), 6 hrs.	+/-1%	0.4%				
Water Absorption	ASTM D471 @158°F (70°C), 1 week	+/-3.0% (top coating only)	0.7%				
Hydrostatic Resistance	ASTM D751 Method D	Not Established	430 psi				
Ozone Resistance	ASTM D1149	No visible deterioration @ 7 x magnification	No visible deterioration @ 7 x magnification				
SRI (Solar Reflectance Index) Initial/Aged	N/A	N/A	94/81 83 Aged Title 24				
Reflectivity (white) Initial/Aged	ASTM C1549 ASTM E903	N/A N/A	0.76/0.68 81.9% Reflectance				
Emissivity (white) Initial/Aged	ASTM C1371 ASTM E403	N/A N/A	0.90/0.83 0.94				
Weather Resistance	ASTM G155/D6878	10,080 KJ/(m² · nm) at 340 nm	>25,000 KJ/(m² · nm) at 340 nm				
Heat Aging	ASTM D573	240°F (115°C) for 32 weeks	60 weeks				
Thickness Above Scrim	ASTM D7635	Min 30% of Total Thickness	22.1 mil (Nominal)				
Guarantee		·					
Up to 25 years							

\*White, Energy Gray, and Energy Tan Membranes Only

\*\*ENERGY STAR® only valid in the U.S.

## **Product Data**

	5′x 100′	6′ x100′	8′x100′	10′x100′	12′x100′		
Roll Size	(1.52 x 30.5 m) (500 sq. ft. [46.5 sq.m])	(1.83 x 30.5 m) (600 sq. ft. [55.74 sq.m])	(2.44 × 30.5 m) (800 sq. ft. [74.3 sq.m])	(3.05 x 30.5 m) (1,000 sq. ft. [92.9 sq.m])	(3.65 × 30.5 m) (1,200 sq. ft. [111.484 sq.m])		
Roll Weight	162 lb. (73.5 kg)	194.4 lb. (88.2 kg)	257 lb. (117 kg)	322 lb. (146.1 kg)	386.4 lb. (175.3 kg)		
Colors	White, Tan, Gray						
Storage	Store rolls on their sides on pallets or shelving in a dry area.						
Safety Warning	Membrane rolls are heavy. Position and install by at least two people.						
Note: Membrane rolls shipped horizontally on pallets, stacked pyramid-style and banded. Product sizes, dimensions, and widths are nominal values and are subject to normal manufacturing/packaging tolerance and variation.							

